

## Nucem Mortar

### Polymer Modified Cementitious Repair Mortar

#### Description

Nucem Mortar is a pre-packed shrinkage compensated, polymer modified cement based mortar supplied with either an acrylic or SBR latex polymer. Nucem Mortar is formulated to comply with the requirements of EN1504 Part 3 Class R4 as well as conform to the DTp Model Specification for the 'Repair of Concrete Highway Structures' BD 27/86 Clause 6. It is based on Portland Cements complying with Clause 1702, DTp Specification for Highway Works and non reactive aggregates. Nucem Mortar is specially designed for the restoration of spalled and damaged concrete caused by reinforcement corrosion or frost attack.

#### Advantages

- Pack contains all constituents including gauging liquid.
- Guaranteed low water/cement ratio.
- Excellent adhesion to dense concrete and steel etc.
- Contains no added chlorides, the total chloride ion content is less than 0.05%.
- Non-reactive aggregates in accordance with DTp Specification for Highway Works Clause 1704-6.
- All contents pre-weighed, dispensing with need for any measurement.
- Excellent workability and finishing properties.
- Good resistance to water, frost & salt penetration.
- Controlled Equivalent Sodium Oxide to less than 3 kg/m<sup>3</sup>.
- Manufactured under BSI QA Scheme, ISO 9001, EN 29001.
- Suitable for next day waterproofing.

#### Applications

- Repair of damaged insitu and precast concrete.
- Repair of damaged floors, bridge decks and road wearing surfaces.
- Screeding where abrasion and/or water resistance is required.
- Repairs to spalled columns and beams using formwork.
- Bedding of concrete or stone paving/kerb units.
- Bedding and raising of manhole frames in carriageways.

 0086	
Nufins, Kingston House, 3 Walton Road, Pattinson North, District 15, Washington, Tyne & Wear. NE38 8QA 13 0086-CPD-594215	
EN 1504-3 Concrete repair product for structural repair PCC Mortar (based on polymer modified hydraulic cement)	
Compressive strength	Class R4 (>45 MPa)
Chloride ion content	≤0.05 %
Adhesive bond strength	>2.0 MPa
Adhesion after freeze/thaw (50 cycles with salt)	>2.0 MPa
Elastic modulus	>20 GPa
Dangerous substances	Complies with 5.4

#### Surface Preparation

The substrate must be clean and sound, hence all grease, oil, dust and laitance must be removed by scarifying. The edges of the repair must be recessed at least 10mm. Where spalling is caused by reinforcement corrosion, all steel must be exposed and cleaned to remove all loose scale and rust, preferably by grit blasting.



## Technical properties of NuceM Mortar

Properties	Standard	Performance Requirement	Declared Value
Appearance			Grey Powder & White Liquid
Chloride-ion content	EN1015-17	≤ 0.05%	≤ 0.05%
Maximum aggregate size			4mm
Water/cement ratio			0.38
Cement content			≥ 400 kg/m <sup>3</sup>
Layer thickness-minimum			10mm
Density			2200 kg/m <sup>3</sup>
Working time			30-45 Minutes
Temperature for application			5°C to 30°C
Compressive strength @ 20°C	EN 12190	≥ 45 MPa	1 Day @ 20 MPa 7 Day @ 40 MPa 28 Days @ 54 MPa
Modulus of elasticity,	EN13412	≥ 20 GPa	≥ 20 GPa
Flexural strength	BS6319-3		10 Mpa
Modulus of elasticity,	BS6319-3		26 GPa
Adhesion - concrete	EN1542	≥ 2.0 MPa	≥ 2.0 MPa
Adhesion after freeze/thaw	EN13687-1	≥ 2.0 MPa	≥ 2.0 MPa
Adhesion after thunder	EN13687-2	≥ 2.0 MPa	≥ 2.0 MPa
Adhesion after dry cycling	EN13687-4	≥ 2.0 MPa	≥ 2.0 MPa
Skid resistance	EN13036-4		Class 1
Carbonation resistance	EN13295	$d_k \leq \text{ref. concrete}$	Passes
Capillary absorption	EN13057	$\leq 0.5 \text{ kg/m}^2/\text{Hr}^{0.5}$	$\leq 0.5 \text{ kg/m}^2/\text{Hr}^{0.5}$
Cracking tendency	Coutinho ring test		No cracking after 180 days

Technical data shown are statistical results and do not correspond to guaranteed minima.

Tolerances are those described in appropriate performance standards.

1 N/mm<sup>2</sup> = 1 MPa

1 kN/mm<sup>2</sup> = 1 GPa

## Priming

Nucem Primer is prepared by adding the contents of the base to the hardener container and mixing thoroughly. Usable life 2 - 3 hours.

The prepared surface and cleaned reinforcement steel should be coated with the Nucem Primer using a stiff brush ensuring it is thoroughly worked into the surface. Nucem Primer can be sprayed using specialist equipment.

When using Nucem Primer it is not normally necessary to pre-saturate the substrate as it may be applied to either dry or damp surfaces. However, when applying a section of less than 20mm thick and the substrate has dried over a substantial period, it is advisable to pre-dampen the surface before priming.

Whilst the primer is still tacky, normally within 3 hours, apply Nucem Mortar. If the primer dries before the application of the Nucem Mortar then the area should be re-primed.

Coverage of Nucem Primer is 3 - 5 m<sup>2</sup> per 1.0 kg pack.

## Mixing

The use of a forced action pan mixer will ensure thorough mixing. Wet the bowl and drain. Add two thirds of the gauging liquid to the mixer then all the powder component and mix for 30-60 seconds. Add all or part of the remaining gauging liquid to bring to the required consistency. Do not over mix.

## Application Instructions

Apply mixed Nucem Mortar to the substrate previously primed with Nucem Primer while the primer is still tacky. Compact the Nucem Mortar to ensure maximum durability and finish as for normal mortar.

All equipment should be cleaned immediately after use by washing with water.

## Curing

Normal curing procedures should be applied immediately after finishing and precautions taken to avoid frost attack. UV degradable resin based curing membranes should not be used if the concrete is to receive a subsequent surface coating.

## Over coating

After a suitable curing period the Nucem Mortar may be over coated with decorative coatings or a waterproof membrane.

## Packaging

Nucem Mortar: 27.5 kg units (yield 13.0 litres approx.)

Nucem Primer: 1.0 kg units (coverage 3 - 5 m<sup>2</sup>) and 0.5 kg units (coverage 1.5 - 2.5 m<sup>2</sup>).

## Storage

Material must be stored unopened in dry, frost free conditions. The shelf life of Nucem Mortar is 6 months.

## Health & Safety

Product Safety Data Sheets (SDS) are available from Nufins. SDS sheets are provided to help customers satisfy their safe handling, use and disposal needs as well as assist with any conformance requirements made locally by health and safety regulations.

SDS are continually updated to provide the latest information to our customers. We therefore recommend contacting our head office to obtain the most recent and accurate SDS before handling and using any product.

## Limitations

The minimum application thickness should be 10mm. Application should not be carried out when the temperature is below 5°C.

## Disclaimer

The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied themselves independently as to the suitability of our products for their own particular purpose. In no event shall Nufins be liable for consequential or incidental damages.

Users must always refer to the most recent issue of the Technical Datasheets, copies of which will be supplied on request.

## Technical Support

Through our technical department and laboratories we can offer a comprehensive service to specifiers and contractors. Technical contacts are available to provide further information and arrange demonstrations