

Epigard

Waterproof Membrane

Description

A two component extended epoxy high build coating characterised by its inbuilt flexibility, excellent adhesion and resistance to water and a wide range of chemicals. Epigard will successfully protect concrete structures including abutments, wing walls and bearing shelves, drainage channels, silos and tanks.

Advantages

- No primer required
- Excellent bond strength
- Good chemical and abrasion resistance
- Inbuilt flexibility


Applications

- Chemically resistant/waterproof protective coating for concrete and steel structures

Technical Information

Type	Epoxy
S.G.	1.3
Pot Life	65 Minutes @ 20°C
Pot Life	>2 Hours @ 5°C
Full Cure	7 Days
Hardness	70 (Shore D)
Coverage	4-6m ² /kg
Dry Film Thickness	170 micron per coat

Tested at 23°C, unless otherwise stated.

 0086	
Nufins, Kingston House, 3 Walton Road, Pattinson North, District 15, Washington, Tyne & Wear, NE38 8QA 13 0086-CPR-594215	
EN 1504-2 Surface protection system for concrete Coating	
Permeability to CO ₂	s _D >50m
Permeability to Water Vapour	Class 1
Capillary Absorption & Permeability to Water	<0.1 kg/m ² /H ^{0.5}
Adhesion	≥1.5 MPa
Dangerous substances	Complies with 5.3

Chemical Resistance

Hydrochloric Acid (Conc.)	Fair
Nitric Acid 25%	Good
Sulphuric acid 50%	Good
Sodium Hydroxide 50%	Good
Ammonia 10%	Good
White Spirit	Good
Methylated Spirit	Good
Xylene	Good
Lubricating Oil	Good
Petrol	Good
Skydrol	Good
Sodium Hypochlorite (Bleach)	Good
Salt (Sodium Chloride saturated)	Good
Ammonium Sulphate 10%	Good



Technical properties of Epigard.

Properties	Standard	Performance Requirements	Declared Value
Appearance			Resinous Coating
Solids Content			>90%
Specific Gravity			1.31
Viscosity			1120 Cps
Working Life			50-65 Minutes
Coverage			4-6m ² /kg
Application Temperature			7°C to 35°C
Maximum intercoat period			48 Hours @ 20°C
Permeability to Water Vapour	EN ISO 7783-1	S _D >50m	S _D >50m (Class III)
Capillary Absorption & Permeability to Water Vapour	EN 1062-3	W<0.1 kg/m ² /Hr ^{0.5}	W<0.1 kg/m ² /Hr ^{0.5}
Tear Strength			>6 MPa
Tensile Strength	BS 2782-3		>8 MPa
Elongation	BS 2782-3		30%
Slip Resistance	EN 13036-4		Class 1
Adhesive bond Strength	EN 1542	>1.5 MPa	>2.0 MPa
Adhesion After Freeze/Thaw (50 Cycles with salt)	EN 13687-1	>1.5 MPa	>2.0 MPa
Adhesion after Thunder Shower (30 Cycles)	EN 13687-2	>1.5 MPa	>2.0 MPa
Adhesion After Dry Cycling (30 Cycles)	EN 13687-4	>1.5 MPa	>2.0 MPa

Technical data shown are statistical results and do not correspond to guaranteed minima.

Tolerances are those described in appropriate performance standards.

All testing was performed at 23°C, unless otherwise specified.

1 N/mm² = 1 MPa

1 kN/mm² = 1 GPa

Surface Preparation

All surfaces should be clean, dry, free from oil, grease and chemical contamination. Oil and grease can be removed using *Desolve*.

Concrete surfaces should be free from laitance, this should be removed by either scarifying, wire brushing or preferably by high pressure water or sand blasting. Blow holes or other surface irregularities should be repaired using *Nupatch Cosmetic* or *Epolite*. Concrete surfaces should be at least 21 days old.

Mixing

Mix only full units. The entire contents of the hardener should be added to the base and mixed thoroughly, avoiding incorporation of air. Care should be taken to prevent unmixed material remaining in the mixing vessel.

Application Instructions

Epigard may be applied by brush, roller or airless spray. The first coat may be tinned with up to 10% *Nuwash* to aid application. Two coats are normally applied. All equipment should be cleaned with *Nuwash* immediately after use.

Packaging

Epigard is available in 5 kg units.

Storage

The shelf life is 12 months when stored unopened in dry, normal conditions and away from direct sunlight. Protect from frost.

If stored in cold conditions the containers should be warmed prior to use as this will assist mixing and application.

Health & Safety

Product Safety Data Sheets (SDS) are available from Nufins. SDS sheets are provided to help customers satisfy their safe handling, use and disposal needs as well as assist with any conformance requirements made locally by health and safety regulations.

SDS are continually updated to provide the latest information to our customers. We therefore recommend contacting our head office to obtain the most recent and accurate SDS before handling and using any product.

Limitations

Do not apply at temperatures below 7°C.

Disclaimer

The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied themselves independently as to the suitability of our products for their own particular purpose. In no event shall Nufins be liable for consequential or incidental damages.

Users must always refer to the most recent issue of the Technical Datasheets, copies of which will be supplied on request.

Technical Support

Through our technical department and laboratories we can offer a comprehensive service to specifiers and contractors. Technical contacts are available throughout the UK to provide further information and arrange demonstrations.